

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claims 1 to 8. (Canceled).

9. (New) A contact surface for an electrical contact, comprising:
an Ag layer galvanically deposited on a copper-based substrate, the Ag layer including finely dispersed graphite particles in a quantity of between 1 and 3 weight % of the Ag layer, the graphite particles having a length in a range of 0.5 to 20 μm .
10. (New) The contact surface according to claim 9, wherein the graphite particles have a length in the range of 1 to 10 μm .
11. (New) The contact surface according to claim 9, wherein the graphite particles have a thickness in the range of 0.05 and 2 μm .
12. (New) The contact surface according to claim 9, wherein a ratio of thickness to length of the graphite particles is in the range of 1:2 to 1:40.
13. (New) The contact surface according to claim 9, wherein the graphite particles are arranged at least one of (a) anisotropically and (b) statistically along a habitus plane of the Ag layer.
14. (New) The contact surface according to claim 9, wherein a layer thickness of the Ag layer is in the range of approximately 1 to approximately 10 μm .
15. (New) The contact surface according to claim 9, wherein the graphic particles do not simultaneously include a maximum thickness and a maximum width.
16. (New) A contact surface for an electrical contact, comprising:
a copper-based substrate; and

an Ag layer galvanically deposited on the copper-based substrate, the Ag layer including finely dispersed graphite particles in a quantity of between 1 and 3 weight % of the Ag layer, the graphite particles having a length in a range of 0.5 to 20 μm .

17. (New) A method, comprising:

providing a contact surface in an automotive plug connection in close proximity to an engine, the contact surface including an Ag layer galvanically deposited on a copper-based substrate, the Ag layer including finely dispersed graphite particles in a quantity of between 1 and 3 weight % of the Ag layer, the graphite particles having a length in a range of 0.5 to 20 μm .